



Thermory's thermally stabilised timbers offer a range of natural or pre-finished, ready to install, cladding and lining solutions. Featuring spruce and pine ranges that are responsibly sourced from sustainably grown plantation timbers. These timbers are thermally modified using heat and steam, to produce a durable, high performing product range that carries a Class 1 durability rating to perform for decades in Australian conditions.

Thermory modifies the timber for increased durability and dimensional stability in a range of natural and prefinished, ready to install exterior cladding and interior lining solutions.

Spruce Cladding Intense: Drift Black Pearl C26



Thermory® timber cladding and lining in a Drift finish offers the rustic look of reclaimed timber, with the performance of a thermally modified timber product. Ideal for a weathered or country design aesthetic, Black Pearl offers a gently worn grey timber tone. Sourced from sustainably managed plantations, the Drift range delivers exceptional durability and dimensional stability to meet the demands of Australian conditions.

Texture

Brushed

Grade

Class 1 Durability
Thermally Stabilised Timber

Colour

Soft Grey tones


Species

Spruce

Size (mm)


186 x 19

C26 Profile:



■ C26: 186 x 19 / cover: 169mm

Corner Thermo - Spruce CP3



■ 42x42

One universal profile for indoor and outdoor usage. Boards with straight-cut ends can be installed without exposing the endgrain.



CLASS 1



Durability
Improved Durability and rot resistance



Stability
Enhanced dimensional stability in changing weather conditions




Chemical-Free
Thermal modification process is entirely natural

Call 1300 399 922
or email info@citytimber.com.au

1400 Centre Rd, Clayton South 3169
citytimber.com.au





DECLARATION OF PERFORMANCE

The undersigned, representing
Thermory AS (Lõõtsa 1a, Tallinn, Harju County, Estonia)
and the manufacturing plant in Loo, Harju County, Estonia
hereby declares that the

THERMALLY MODIFIED SOLID WOOD SPRUCE CLADDING AND PANELING WITHOUT SURFACE COATING

is in conformity with the provisions of the EC Regulation No 305/2011
Construction Product Regulation system of assessment and verification of
constancy of performance: System 3 and is in accordance with the requirements of
EN 14915:2013

„Solid wood panelling and cladding – Characteristics,
evaluation of conformity and marking“
Initial type testing report No.01_THERMORY_EN14915

CHARACTERISTIC	PERFORMANCE DECLARATION
Species	Nordic spruce (<i>Picea abies</i>)
Intended use	For exterior and interior use
Density and range of thickness	400 kg/m ³ , 18–42 mm
Reaction to fire	D-s1, d0 (tested according to standard EN14915:2013)
Emission of formaldehyde	E1
Content of pentachlorophenol	NPD
Release of other dangerous substances	NPD
Water vapor permeability	NPD
Thermal resistance	0,12 W/(m K)
Sound absorption	NPD
Biological durability (according to CEN/TS 15083-1:2005)	Class 1, when thermally modified (215 °C, Intense)



Liivi Viin
CQO
Tallinn 08.04.2022